

AD-A106 541

BROWN UNIV PROVIDENCE RI DEPT OF CHEMISTRY

F/6 7/2

PREPARATION AND CHARACTERIZATION OF CONDUCTING IRON TUNGSTATES.(U)

OCT 81 H LEIVA, K DWIGHT, A WOLD

N00014-77-C-0387

UNCLASSIFIED TR-17

NL

1 OF 1
AD-A
106 541



END

DATE

FILED

11-81

DTIC

AD A106541

DTIC FILE COPY

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 17	2. GOVT ACCESSION NO. AD A106 541	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Preparation and Characterization of Conducting Iron Tungstates	5. TYPE OF REPORT & PERIOD COVERED Technical	6. PERFORMING ORG. REPORT NUMBER 141 77-17
7. AUTHOR(S) H./Leiva, K./Dwight and Wold	8. CONTRACT OR GRANT NUMBER(s) N00014-77-C-0387	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Professor Aaron Wold Brown University, Department of Chemistry Providence, R. I. 02912	10. PROGRAM ELEMENT PROJECT, TASK AREA & WORK UNIT NUMBERS NR-359-653	
11. CONTROLLING OFFICE NAME AND ADDRESS Dr. David Nelson, Code 472 Office of Naval Research Arlington, Virginia 22217	12. REPORT DATE October 23, 1981	13. NUMBER OF PAGES 26
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report)	15a. DECLASSIFICATION DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Submitted to the Journal of Solid State Chemistry		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Iron Tungstates Tri- α -PbO ₂ Photoanodes		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Several iron(III) tungstates have been prepared, and their crystallographic, magnetic, electric and photoelectronic properties have been characterized. The compounds crystallize with the tri- α -PbO ₂ structure, and the actual ordering of the MO ₆ octahedra (M=Fe or W) appears to determine these properties. Under illumination, Fe ₂ WO ₆ photoanodes show an intermediate photoresponse between conducting α -Fe ₂ O ₃ and WO ₃ , although the flat-band potential is still too positive.		

DTIC
ELECTE
NOV 2 1981
A

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

81 10 20 000

OFFICE OF NAVAL RESEARCH

Contract N00014-77-C-0387

Task No. NR-359-653

TECHNICAL REPORT NO. 17

Preparation and Characterization of Conducting Iron Tungstates

by

H. Leiva, K. Dwight, and A. Wold

Prepared for Publication
in the
Journal of Solid State Chemistry

Brown University
Department of Chemistry
Providence, Rhode Island

October 23, 1981

For	
1	
2	
3	
4	
5	
6	
7	
8	
9	
10	
11	
12	
13	
14	
15	
16	
17	
18	
19	
20	
21	
22	
23	
24	
25	
26	
27	
28	
29	
30	
31	
32	
33	
34	
35	
36	
37	
38	
39	
40	
41	
42	
43	
44	
45	
46	
47	
48	
49	
50	
51	
52	
53	
54	
55	
56	
57	
58	
59	
60	
61	
62	
63	
64	
65	
66	
67	
68	
69	
70	
71	
72	
73	
74	
75	
76	
77	
78	
79	
80	
81	
82	
83	
84	
85	
86	
87	
88	
89	
90	
91	
92	
93	
94	
95	
96	
97	
98	
99	
100	

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited

INTRODUCTION

Since the discovery by Fujishima and Honda¹ that an n-type TiO_2 electrode could be used for the photoinduced electrolysis of water, there has been a large effort spent in the search for more efficient photoanodes. Several studies²⁻¹⁰ have reported the use of iron(III) oxide and tungsten(VI) oxide as potential candidates as photoanodes. These compounds have been found to be stable in aqueous solutions and possess optical band gaps of about 2.2 eV (Fe_2O_3) and 2.7 eV (WO_3). Although these band gaps allow for greater utilization of the solar spectrum than TiO_2 (Eg \sim 3.1 eV), their flat-band potentials of 0.7V (Fe_2O_3) and 0.5V (WO_3) (referred to a reversible hydrogen electrode at pH = 13.3)⁶ require a large applied bias before photoinduced electrolysis occurs. In the search for other oxides having relatively small band gaps and also small flat-band potentials, some iron-containing ternary systems have been investigated.¹¹ It was found, by comparison with the alkaline-earth niobates, that FeNbO_4 , which crystallizes with the wolframite structure, showed the highest photoresponse, which was due to $[\text{FeO}_6]$ active centers. Since $[\text{WO}_6]$ octahedra must be responsible for the quantum efficiency observed in WO_3 photoanodes, compounds containing both $[\text{FeO}_6]$ and $[\text{WO}_6]$ octahedra may be expected to show improved photoresponse.

In this study, Fe_2WO_6 and several other iron-tungstates fulfilling these structural criteria have been prepared, and some of their photoelectronic as well as their crystallographic, magnetic, and electric properties have been characterized.

EXPERIMENTAL

Synthesis. All of the iron(III) tungstates were prepared from the solid state reactions between Fe_2O_3 (formed by decomposition in air of iron(II) oxalate) and WO_3 (prepared by heating 99.99% pure tungsten foil under flowing oxygen for 80 h at 1000°C). A finely ground mixture of appropriate amounts of the starting materials was placed in a covered platinum crucible and heated in air at 950°C for 92-126 h. FeWO_4 was prepared at 925°C in sealed evacuated silica tubes by reacting WO_3 and FeO , which was obtained by reacting Fe_2O_3 and iron metal. Each sample was x-rayed, reground, and then reheated. After the last heating, the product was removed rapidly from the furnace, allowed to cool to room temperature, and reexamined by x-ray analysis. This was done in order to confirm the formation of a single phase, as well as to determine cell parameters. A Philips-Norelco diffractometer with $\text{CuK}\alpha_1$ radiation ($\lambda = 1.5405\text{\AA}$) was used at a scan rate of 0.25 degree $2\theta/\text{min}$ and a chart speed of 30 inch/h. Cell parameters were obtained from refinement of the data with the aid of a computer.

Discs were formed by hot-pressing aliquots of approximately 800 mg for 2 h at 980°C at an applied pressure of 5000 psi. For this purpose, dies and plungers of Diamonite (Al_2O_3) were used. The heating rate was about $12^\circ\text{C}/\text{h}$, and at the end of the sintering process, the discs were allowed to cool at nearly the same rate. Under these conditions, discs with a surface of about 1.3 cm^2 and a thickness of 0.09 cm were obtained. They were x-rayed with

FeK α radiation (1.9360 \AA), using the Debye-Scherrer method, and their films were compared to those of the corresponding polycrystalline starting compounds to confirm that the phases did not undergo any changes during the sintering process.

Magnetic Measurements. Magnetic susceptibilities were measured using a Faraday balance^{12,13} at a field strength of 10.4 kOe. The data then were corrected for core diamagnetism.¹⁴

Electrical Measurements. The resistivities of the samples were measured using the van der Pauw technique.¹⁵ Contacts were made by the ultrasonic soldering of indium directly onto the samples, and their ohmic behaviors were established by measuring their current-voltage characteristics. The sign of the majority carriers was determined from qualitative measurements of the Seebeck effect.

Photoelectrolytic Measurements. Photoanodes were prepared by evaporating thin films of gold on the backs of the sintered discs to provide good electrical contact. The gold face of each disc was attached to the electrode by means of indium solder, and all but the front surfaces were coated with an electrically insulating resin (Microstop, Michigan Chrome Chemical Corp). The photoelectrolysis measurements were carried out with a 150 watt Xenon lamp, a monochromator (Oriel Model 7240), a glass cell with a quartz window,

and a current amplifier as described previously.¹⁶ A platinized platinum electrode of large surface area served as the cathode. All voltage measurements were made with reference to a saturated calomel electrode (SCE). The electrolyte, 0.2 M sodium acetate (pH = 7.8), was purged of dissolved oxygen by continuous bubbling of 85% argon/15% hydrogen gas.

RESULTS AND DISCUSSION

Structure and Crystallography. Several reports exist concerning the structure of Fe_2WO_6 .¹⁷⁻²¹ Basically, this compound has been reported to crystallize with the columbite structure when prepared below 800°C ,²⁰ and with the tri- $\alpha\text{-PbO}_2$ structure when prepared at higher temperatures.^{19,21} Both of these structures may be regarded as superlattice variants of the fundamental $\alpha\text{-PbO}_2$ structure. They consist of hexagonal close-packed planes of O^{2-} anions in which only half of the octahedral sites are occupied by the metal atoms, Fe or W. The fundamental difference between both structures is in the nature of the 2:1 cation ordering. As shown in Figure 1, for Fe_2WO_6 with the tri- $\alpha\text{-PbO}_2$ structure, each of the resulting octahedra shares a pair of skew edges in such a way that zigzag chains are formed parallel to the c-direction. Senegas and Galy²¹ have indicated that ideally one third of these zigzag chains contain only iron atoms, and two thirds of the chains show a 1:1 ordering of iron and tungsten atoms. In the columbite structure, the ordering is such that each zigzag chain contains only one type of metal (either iron or tungsten), and so there are twice as many zigzag chains with iron atoms as with tungsten atoms. When compared to the $\alpha\text{-PbO}_2$ structure, the 2:1 cation order causes a tripling of the b-parameter in the tri- $\alpha\text{-PbO}_2$ structure, and of the a-parameter in the columbite.

In this study, it was not possible to obtain the columbite variant of Fe_2WO_6 as a pure single phase, since the tri- $\alpha\text{-PbO}_2$ variant also appears to

form at low temperatures. Once the tri- α - PbO_2 structure forms, long anneals even at temperatures below 800°C are unsuccessful in changing the structural ordering. When these samples were heated up to about 800°C in a differential scanning calorimeter, there was no indication of any phase transition. Consequently, Fe_2WO_6 samples were prepared at 950°C , since at this temperature the tri- α - PbO_2 structure is well crystallized.

It also was determined by x-ray diffraction that Fe_2WO_6 cannot be prepared without the appearance of a small amount of α - Fe_2O_3 in the product, as indicated by the presence of some of the strongest reflections of this oxide (012, 110, 024, 116, 214) near the limit of detection. These small peaks could be observed in products prepared at lower temperatures than 950°C . Analogous results were also observed when the preparations were attempted in a sealed silica tube. Similar observations have been reported for other iron-containing ternary systems where the compounds crystallize with the wolframite and columbite structures.¹¹ In these studies, the iron(III)-containing phase forms a solid solution with a phase containing iron(II), and both structures can be derived from the α - PbO_2 framework, and are closely related to the tri- α - PbO_2 structure. Hence, the presence of trace quantities of α - Fe_2O_3 in the attempted preparation of pure Fe_2WO_6 is consistent with the solid solution of small amounts of FeWO_4 . Further evidence for the existence of a solid solution between Fe_2WO_6 and FeWO_4 was obtained by preparing a product having a nominal composition $\text{Fe}_{1.97}\text{W}_{1.03}\text{O}_6$. The resulting material maintained the tri- α - PbO_2 structure.

In addition, the disappearance of the small peaks of $\alpha\text{-Fe}_2\text{O}_3$ could be achieved when iron(III)-deficient compounds were prepared, corresponding to members of the system $\text{Fe}_{2-2x}^{\text{W}}\text{Fe}_{1+x}\text{O}_6$. On increasing the value of x , the $\alpha\text{-Fe}_2\text{O}_3$ peaks decreased in intensity, and for the composition $\text{Fe}_{1.92}^{\text{W}}\text{Fe}_{1.04}\text{O}_6$, a phase free of detectable $\alpha\text{-Fe}_2\text{O}_3$ was obtained. All compounds belonging to this system also crystallized in the tri- $\alpha\text{-PbO}_2$ structure.

Fe_2WO_6 prepared in this study was orthorhombic (space group Pbcn) and the following cell constants were determined: $a=4.577(\text{\AA})$, $b=16.75(\text{\AA})$, $c=4.965(\text{\AA})$. These results are in good agreement with those previously reported.²¹

Magnetic Properties. The magnetic structure of Fe_2WO_6 from 4.2 to 300K has been studied by Pinto et al.²² They reported an antiferromagnetic ordering at 4.2K and a Neel temperature of approximately 240K. Thus, it is not surprising that the dependence of inverse magnetic susceptibility with temperature for Fe_2WO_6 , as shown in Figure 2, is not completely linear at high temperature. However, above 600K the susceptibility does approach linear behavior, and can be interpreted to yield a Curie-Weiss constant of about -450K and an effective molar Curie constant of 7.7 ($\text{emu mole}^{-1}\text{K}$). This value corresponds to a spin-only moment of about 5.6 BM, which is in close agreement with the spin-only value of 5.9 BM for Fe^{3+} ($S=5/2$). The higher slope observed below 600K

indicates the presence of both ferro and antiferromagnetic interactions in Fe_2WO_6 , which would be consistent with the reported magnetic structure.²²

Electrical Properties. A recent report²³ has indicated that Fe_2WO_6 is a p-type semiconductor. However, this study indicates that Fe_2WO_6 , $\text{Fe}_{1.96}\text{W}_{1.02}\text{O}_6$, and $\text{Fe}_{1.92}\text{W}_{1.04}\text{O}_6$, as well as $\text{Fe}_{1.97}\text{W}_{1.03}\text{O}_6$, are all n-type semiconductors. Pure samples of Fe_2WO_6 , $\text{Fe}_{1.96}\text{W}_{1.02}\text{O}_6$, and $\text{Fe}_{1.92}\text{W}_{1.04}\text{O}_6$ would be expected to have high electrical resistivities. However, the measured resistivities at room temperature ranged between 41-59 ohm cm. This observed conductivity is consistent with the presence of Fe(III) and some Fe(II) on equivalent sites. The conductivity of an iron tungstate containing relatively large amounts of Fe(II), i.e., the composition $\text{Fe}_{1.97}\text{W}_{1.03}\text{O}_6$, gave a measured resistivity value in the same range as the other tungstates. This result seems to indicate the existence of some degree of disorder between the iron and tungsten atoms within the chains of the tri- α - PbO_2 structure when the 2:1 ratio of these atoms is changed.

Photoelectronic Properties. The photoresponse observed for several iron tungstates is represented in Figure 3, where the photocurrents obtained in the "white" light are plotted against the anode potential. For Fe_2WO_6 and $\text{Fe}_{1.92}\text{W}_{1.04}\text{O}_6$, transient photocurrents were observed between 0.05-0.5 volts, and only the instantaneous responses were recorded in the plot. As can be seen,

the largest photocurrents are reached for Fe_2WO_6 and decrease on increasing the tungsten and vacancy concentration. The resistivities of these compounds were shown to be similar, and the observed difference of photo-response between Fe_2WO_6 and the tungsten-rich compounds might be due to the introduction either of vacancies, which can act as recombination centers, or of tungsten ions into the predominantly iron chains. Thus, the existence of either vacancies or disorder between iron and tungsten atoms within the zigzag chains would result in a decrease in the photo-response. Thus, for the composition $\text{Fe}_{1.97}\text{W}_{1.03}\text{O}_6$, the observed photocurrents were low. The general shape of the curves observed for Fe_2WO_6 and $\text{Fe}_{1.96}\text{W}_{1.02}\text{O}_6$ are similar to those reported for other iron compounds.¹¹ The onset of photocurrents is not sufficiently abrupt for a reliable determination of the flat-band potentials. The photoresponse cannot be obtained below an anode potential ranging from 0.1 to 0.4 volts versus SCE at pH + 7.8. These values appear to be similar to the potentials reported for conducting Fe_2O_3 and WO_3 samples.^{3,8}

The quantum efficiency (in electrons/photon) of Fe_2WO_6 and $\text{Fe}_{1.96}\text{W}_{1.02}\text{O}_6$, as measured at an anode potential of 0.8 volts versus SCE, is plotted in Figure 4 against the wavelength of the incident light. For both compounds,

the shape of the curves are similar, but the Fe_2WO_6 sample has a higher response at longer wavelengths. The photoresponse observed for these iron tungstates is nearly ten times greater than those reported for conducting $\alpha\text{-Fe}_2\text{O}_3$, but not as large as the maximum response obtained for conducting WO_3 electrodes.^{7,10}

CONCLUSIONS

Fe_2WO_6 and other related iron(III)-deficient tungstates corresponding to members of the ternary system $\text{Fe}_{2-2x}\text{W}_{1+x}\text{O}_6$ have been prepared, and crystallize with the tri- α - PbO_2 structure. The building blocks on this framework are MO_6 octahedra ($\text{M} = \text{Fe}$ or W), and the ordering of these units appears to affect significantly the magnetic, electric, and photoelectronic properties of these compounds. Any deviation from the ideal ordering of these MO_6 octahedra may introduce $[\text{WO}_6]$ octahedra into the zigzag chains expected to contain only FeO_6 units. This disorder must affect any electron transfer process occurring within these chains, and hence the magnitude of the electrical resistivities and, together with any vacancies present, the quantum efficiencies.

The best photoresponse to "white" irradiation is obtained when the anode is made of Fe_2WO_6 ; its magnitude is larger than the values obtained from electrodes made of conducting α - Fe_2O_3 , but lower than the maximum reported for WO_3 . Although the efficiency of Fe_2WO_6 photoanodes is enhanced at long wavelengths, the flat-band potential remains too positive for any practical application.

Measurement of the magnetic susceptibilities at high temperatures above 600K yields an effective molar Curie constant whose value corresponds closely to that expected for spin-only Fe^{3+} ions. In addition, the large, negative Curie-Weiss constant indicates the existence of strong antiferromagnetic interactions in Fe_2WO_6 .

ACKNOWLEDGEMENT

Acknowledgement is made to the Office of Naval Research, Arlington, Virginia for the support of Hector Leiva and Kirby Dwight, and to Brown University's Materials Research program for the use of its laboratory facilities.

REFERENCES


1. A. Fujishima and K. Honda; Nature 238, 37 (1972).
2. K.L. Hardee and A.J. Bard; J. Electrochem. Soc. 123, 1024 (1976).
3. R.K. Quinn, R.D. Nasby and R.J. Baughman; Mat. Res. Bull. 11, 1011 (1976).
4. K.L. Hardee and A.J. Bard; J. Electrochem. Soc. 124, 215 (1977).
5. L.R. Yeh and N. Hackerman; J. Electrochem. Soc. 124, 833 (1977).
6. H.H. Kung, H.S. Jarrett, A.W. Sleight, and A. Ferretti; J. Appl. Phys. 48, 6, 2463 (1977).
7. P. Merchant, R. Collins, R. Kershaw, K. Dwight, and A. Wold; J. Solid State Chem. 27, 307 (1979).
8. M. Butler, R. Nasby and R. Quinn; Solid State Communications 19, 1011 (1976).
9. G. Hodes, D. Cahen, and J. Manassen; Nature 26, 312 (1976).
10. C.E. Derrington, W.S. Godek, C.A. Castro, and A. Wold; Inorg. Chem. 17, 977 (1978).
11. J. Koenitzer, B. Khazai, J. Hormadaly, R. Kershaw, K. Dwight, and A. Wold; J. Solid State Chem. 35, 128 (1980).
12. B. Morris and A. Wold; Rev. Sci. Inst. 39, 1937 (1968).
13. A.W. Catalano, Ph.D. Thesis, Brown University (1973).
14. P.W. Selwood, "Magnetochemistry," 2nd Ed., Intersc. Pub. Co. (1956).
15. L.J. van der Pauw, Philips Res. Rep. 13, 1 (1968).
16. S.N. Subbarao, Y.H. Yun, R. Kershaw, K. Dwight, and A. Wold; Inorg. Chem. 18, 488 (1979).
17. G. Bayer; Ber. Dtsch. Keram. Ges. 39, 535 (1962).
18. V.K. Trunov and L.M. Kovba; Izv. Akad. Nauk. S.S.S.R. 2 (1), 151 (1966).

REFERENCES (Continued)


19. J. Galy and J. Senegas; C.R. Acad.Sc. Paris, C, 275, 665 (1972).
20. C. Parant, J.C. Bernier, and A. Michel; C.R. Acad.Sc. Paris, C, 276, 495 (1973).
21. J. Senegas and J. Galy; J. Solid State Chem. 10, 5 (1974).
22. H. Pinto and M. Melamud; Acta Cryst. A33, 663 (1977).
23. A. Bharati, R.A. Singh; J. Mat. Sciences 16, 511 (1981).

FIGURE CAPTIONS

- Figure 1 Tri- α - PbO_2 structure of Fe_2WO_6 :
 (a) packing of MO_6 octahedra; (b) closest-packed
 layer of oxygen around Fe and W atoms.
- Figure 2 Thermal variation of the inverse molar magnetic
 susceptibility of iron tungstate. The high-
 temperature slope corresponds to a μ_{eff} of
 5.6 BM.
- Figure 3 Variation of photocurrent with anode potential for
 members of the system $\text{Fe}_{2-2x}\text{W}_{1+x}\text{O}_6$ in 0.2M sodium
 acetate (pH=7.8) under "white" Xenon arc irradi-
 tion of 1.0 W/cm^2 .
- Figure 4 Spectral variation of the quantum efficiency (in
 electrons/photon) obtained for members of the
 system $\text{Fe}_{2-2x}\text{W}_{1+x}\text{O}_6$ in 0.2M sodium acetate (pH=7.8)
 at an anode potential of 0.8V with respect to SCE.







(a)




(b)

● Fe ⊗ W







TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Attn: Code 472 801 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Western Regional Office Attn: Dr. R. J. Marcus 1011 East Green Street Pasadena, California 91106	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Eastern Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Commander, Naval Air Systems Command Attn: Code 3100 (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20320	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
		Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. Paul Delahay Department of Chemistry New York University New York, New York 10003	1	Dr. P. J. Hendra Department of Chemistry University of Southampton Southampton SO9 5NH United Kingdom	1
Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 44106	1	Dr. Sam Perone Department of Chemistry Purdue University West Lafayette, Indiana 47907	1
Dr. D. N. Bennion Department of Chemical Engineering Brigham Young University Provo, Utah 84602	1	Dr. Royce W. Murray Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1
Dr. R. A. Marcus Department of Chemistry California Institute of Technology Pasadena, California 91125	1	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
Dr. J. J. Auburn Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. C. E. Mueller The Electrochemistry Branch Materials Division, Research & Technology Department Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910	1
Dr. Adam Heller Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. G. Goodman Globe-Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. Katan Lockheed Missiles & Space Co, Inc. P.O. Box 504 Sunnyvale, California 94088	1	Dr. J. Boechler Electrochimica Corporation Attention: Technical Library 2485 Charleston Road Mountain View, California 94040	1
Dr. Joseph Singer, Code 302-1 NASA-Lewis 21000 Brookpark Road Cleveland, Ohio 44135	1	Dr. P. P. Schmidt Department of Chemistry Oakland University Rochester, Michigan 48063	1
Dr. B. Brummer EIC Incorporated 55 Chapel Street Newton, Massachusetts 02158	1	Dr. H. Richtol Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1
Library P. R. Mallory and Company, Inc. Northwest Industrial Park Burlington, Massachusetts 01803	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. A. B. Ellis Chemistry Department University of Wisconsin Madison, Wisconsin 53706	1	Dr. R. P. Van Duyne Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. M. Wrighton Chemistry Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. B. Stanley Pons Department of Chemistry University of Alberta Edmonton, Alberta CANADA T6G 2G2	1
Larry E. Plew Naval Weapons Support Center Code 30736, Building 2906 Crane, Indiana 47522	1	Dr. Michael J. Weaver Department of Chemistry Michigan State University East Lansing, Michigan 48824	1
S. Rubv DOE (STOR) 600 E Street Washington, D.C. 20545	1	Dr. R. David Rauh EIC Corporation 55 Chapel Street Newton, Massachusetts 02158	1
Dr. Aaron Wold Brown University Department of Chemistry Providence, Rhode Island 02192	1	Dr. J. David Margerum Research Laboratories Division Hughes Aircraft Company 3011 Malibu Canyon Road Malibu, California 90265	1
Dr. R. C. Chudacek McGraw-Edison Company Edison Battery Division Post Office Box 28 Bloomfield, New Jersey 07003	1	Dr. Martin Fleischmann Department of Chemistry University of Southampton Southampton SO9 5NH England	1
Dr. A. J. Bard University of Texas Department of Chemistry Austin, Texas 78712	1	Dr. Janet Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. M. M. Nicholson Electronics Research Center Rockwell International 3370 Miraloma Avenue Anaheim, California	1	Dr. R. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. Donald W. Ernst Naval Surface Weapons Center Code R-33 White Oak Laboratory Silver Spring, Maryland 20910	1	Mr. James R. Moden Naval Underwater Systems Center Code 3632 Newport, Rhode Island 02840	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. R. Nowak Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. Bernard Spielvogel U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709	1
Dr. John F. Houlihan Shenango Valley Campus Pennsylvania State University Sharon, Pennsylvania 16146	1	Dr. Denton Elliott Air Force Office of Scientific Research Boiling AFB Washington, DC 20332	1
Dr. D. F. Shriver Department of Chemistry Northwestern University Evanston, Illinois 60201	1	Dr. David Aikens Chemistry Department Rensselaer Polytechnic Institute Troy, NY 12181	1
Dr. D. H. Whitmore Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. A. P. B. Lever Chemistry Department York University Downsview, Ontario M3J1P3 Canada	1
Dr. Alan Bewick Department of Chemistry The University Southampton, SO9 5NH England	1	Mr. Maurice F. Murphy Naval Sea Systems Command 63R32 2221 Jefferson Davis Highway Arlington, VA 20360	1
Dr. A. Himy NAVSEA-5433 NC #4 2541 Jefferson Davis Highway Arlington, Virginia 20362	1	Dr. Stanislaw Szpak Naval Ocean Systems Center Code 6343 San Diego, CA 95152	1
Dr. John Kincaid Department of the Navy Strategic Systems Project Office Room 901 Washington, DC 20376	1	Dr. Gregory Farrington Department of Materials Science & Engineering University of Pennsylvania Philadelphia, PA 19104	1
M. L. Robertson Manager, Electrochemical Power Sonics Division Naval Weapons Support Center Crane, Indiana 47522	1	Dr. Bruce Dunn Department of Engineering & Applied Science University of California Los Angeles, CA 90024	1
Dr. Elton Cairns Energy & Environment Division Lawrence Berkeley Laboratory University of California Berkeley, California 94720	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359No.
Copies

Dr. Micha Tomkiewicz
Department of Physics
Brooklyn College
Brooklyn, NY 11210 1

Dr. Lesser Blum
Department of Physics
University of Puerto Rico
Rio Piedras, PR 00931 1

Dr. Joseph Gordon II
IBM Corporation
K33/281
5600 Cottle Road
San Jose, CA 95193 1

Dr. Robert Somoano
Jet Propulsion Laboratory
California Institute of Technology
Pasadena, CA 91103 1

DATE
ILME